



CAPELLADA ATANADO NR - SEMITERMINADO/IGUALIZADO

FICHAS TECNICAS DE PRODUCTOS
FIT-LT-035 - Rev.: 04
Fecha Publ.: 08-08-2022

PRODUCT : SHOES UPPER							
Description			GROUP:		CAPELLADA		
			ARTICLE:		ATANADO NR		
			CUSTOMER:		STANDARD		
			REFERENCE:		PDC-LT-010		
CHARACTERISTICS	VALUE Semi	VALUE Igual.	UNIT OF MEASUREM NT	TOLERANCE	STANDARD APPLIED	METHOD USED	CLASSIFICATION OF CHARACTERISTIC
PH (Ph)	3,9 +0,5		---	---	ASTM D 2810	MEL-07-087	---
HUMIDITY PERCENTAGE (Porc. de Humedad) **	14-18	10 - 16	%	---	ASTM D 3790	MET-07-063 MET-07-064	---
CHROME (Cromo)	4 ± 0.7		%	---	ISO 5398-1	MEL-LT-093	---
FAT CONTENT (Contenido grasa)	6 ± 3		%	---	ASTM D 3495	MEL-LT-094	---
SOFTNESS ϕ 25mm (Toque) **	NECK 1,2 - 1,7 BUTT 1,5 - 2,0		SOFTNESS TEST	---	ISO 17235	MEL-LT-066	◇
TENSILE STRENGHT (Resist. a la tracción)	7.0		N/mm²	min.	ISO 3376	MEL-LT-111	◇
ELONGATION (Elongación)	50		%	max.	ISO 3376	MEL-LT-111	◇
TONGUE TEAR (Resist. al desgarr)	6		lbs	min.	ISO 3377-1	MEL-LT-104	◇
BALL BRUST TEST (Lastometro/Estallido de flor)	10		kg	min.	ISO 3379	MET-07-082	◇
	7		mm				
FORMALDEHYDE CONTENT (Cont.de formaldehido) *	75		ppm	max.	DIN EN ISO TS 17226-1	EXTERNAL LABORATORY	◆
RESTRICTED SUBSTANCES (Sust. restringidas) *	<i>According to EDP-LT-001 (*)</i>					EXTERNAL LABORATORY	◆
NOTE:	<p>FREQUENCY OF TEST DECLARED IN FOP-LT-002 ** Control needed to lot approval before final inspection (The other tests could be reported at the customer after shipment). Ref. FOP-LT-060 /FOP-LT-019</p> <p>References: ◇ Particular requirements of customers or Technical definition (expertise). ◆ Effect on the user or legal compliance.</p>						

Autor:
Mariela Aranda(Responsable de PCD)

Revisor: Alejandro Bertran(Coordinador Técnico)

Publicado por: Gabriela Quiroga(Gerente de Calidad)